



Dirasol Direct Projection Emulsions

S10 - SW10 - H10 - S5 - SW5 - SUPERPRO

The Dirasol range of Direct Projection Emulsions has been developed to provide high quality stencils for all screen printing applications.

Main Characteristics							
Dirasol >	S10	S10 RED	SW10	H10	S5	SW5	SuperPro
Recommended Application	Large Poster & Banner	Large Poster & Banner	Large Poster & Banner	Poster & PoP	Poster & PoP	Poster & PoP	Poster & PoP
Magnification Range	x7-x12	x7-x12	x7-x12	x4-x12	x3-x10	x3-x7	x3-x5
Ink Resistance	Solvent & Conventional UV	Solvent & Conventional UV	Solvent, Conventional/ Water-based UV	Solvent & Conventional UV	Solvent & Conventional UV	Solvent, Conventional/ Water-based UV	Solvent, Conventional/ Water-based UV
Emulsion Type	Pre-sensitised (Blue)	Pre-sensitised (Red)	Pre-sensitised (Blue)	Pre-sensitised (Blue)	Pre-sensitised (Blue)	Pre-sensitised (Blue)	Two Pack (Violet)
Definition	Fair	Fair	Good	Good	Excellent	Excellent	Excellent
Resolution	Excellent	Excellent	Good	Excellent	Excellent	Excellent	Excellent
Ease of washout & reclaim	Good	Excellent	Fair	Excellent	Good	Fair	Good
Solids Content	25%	25%	34%	28%	32%	36%	40%
Stencil Build in microns	0*	0*	1**	1**	2**	2**	2**
Viscosity @ 25° (mPas)	3,200	3,200	4,500	4,500	5,700	5,500	5,500 (sensitised)

* 1+1 coating on 120 mesh. ** 1+1 coating on 150 mesh

Product Overview

Dirasol S10

Designed for high magnification poster and billboard applications, S10 is particularly suitable where fast exposure speed is required.

Dirasol S10 Red

A fast exposing emulsion for high magnification poster and billboard applications, S10 Red is also quick and easy to develop, even if screens have been coated for several days.

Dirasol SW10

Universal projection emulsion for all ink types, SW10 is particularly suited for high magnification poster and billboard applications using water-based or water-based UV inks.

Dirasol H10

Suitable for all magnification ranges, including PoP and poster, H10 has superb print resolution and definition alongside excellent coating characteristics, even with 1+0 coatings. H10 works with solvent based and conventional UV inks, and is extremely easy to develop and decoat.

Dirasol S5

A higher solids emulsion for lower magnification, higher quality PoP work using solvent-based or conventional UV inks.

Dirasol SW5

A higher solids emulsion with universal ink resistance, particularly suitable for high quality PoP work using water-based or water-based UV inks.

Dirasol SuperPro

For the highest print quality and best on-press durability, with resistance to all ink types. As SuperPro is a dual cure emulsion, and has an exposure speed much slower than one pot emulsions, SuperPro is only recommended for use at low magnification levels, and with high light output projection cameras, such as Proditec and Svecia.

Safelighting

All handling of Dirasol projection emulsions should be carried out in light which is low in blue and ultra-violet content. A photographic safelight is not essential but it is desirable to use yellow illumination as provided by gold fluorescent tubes.

Daylight must be excluded or filtered by a yellow lacquer coating or film applied over windows.

Dirasol Direct Projection Emulsions

S10 - SW10 - H10 - S5 - SW5 - SUPERPRO

Sensitising (SuperPro only)

Dirasol SuperPro is supplied as a two-pack system consisting of:

Part A - coloured emulsion

Part B - diazo sensitiser

which should be mixed as follows:

1. Add water to the sensitiser bottle, to not less than 80% of its total capacity, and shake until the sensitiser is fully dissolved.
2. Add the sensitiser solution to Part A and thoroughly stir. Ideally the emulsion should be allowed to de-gas for one hour before use.

Pre-sensitised emulsions may require a gentle stir to disperse any condensation formed at the top of the bucket.

Preparing the Screen

Degrease the mesh in automatic screen cleaning machines using Xtend Prep 300 Sprayable Degreasing Concentrate or by hand with Prep 102 Degreasing and Emulsifying Concentrate.

When using Prep 102, wet the screen and apply with a sponge or brush and then rub the mesh with a light circular motion. Ensure that both sides of the screen are thoroughly treated. Leave to stand for a few minutes and rinse with cold water to remove all traces of Prep. Allow the mesh to dry before coating.

New mesh requires a diazo wash to optimise emulsion adhesion. Mix Sericol diazo syrup (SZM02/0980) with 5 litres of water and apply to both sides of mesh and then thoroughly rinse with water.

Coating

Automatic Coating:

One simultaneous single coat on each side of the screen is recommended, followed by further coats on the squeegee side if required to increase build.

Hand coating:

Apply 1 coat on the print side of the screen and then apply one coat or more wet-on-wet on the squeegee side. The Sericol Coating Trough is particularly recommended.

Sericol Coating Troughs

The troughs are composed of precision extruded aluminium channelling fitted with injection moulded end pieces for accurate and consistent coating of photostencil emulsions. The channelling has a hard anodised finish which effectively seals the surface, easing cleaning and protecting from corrosion. The ends have a special shoulder and slots incorporated, ensuring the coating edge is consistently at the optimum angle to the screen helping eliminate beads. These features permit relatively inexperienced operators to coat screens faster and more accurately. Designed to deposit medium coating thicknesses, it is possible to coat a screen to a given stencil thickness with fewer strokes than would be required with a sharper or less precise edge. The amount of emulsion used to coat a given area of screen is principally governed by the fineness of the mesh. Sericol Coating Troughs hold sufficient to cover approximately 1.5-2m in a single stroke.

Drying

Dry the screen in a horizontal position, squeegee side up in darkness or subdued yellow light. A warm air fan or heated cupboard (up to 40°C) may be used but care should be taken not to blow dust on to the drying screen. Screens may be stored in the dark at cool temperatures prior to exposure. For optimum resolution of fine halftones it is better to rotate the screens so that they all dry in approximately the same time.

Exposure

Correct exposure time is most important to obtain optimum definition/resolution and stencil life. Correct exposure can vary widely depending on a number of factors. For this reason it must be determined by the use of the 'step and repeat' test exposure method. This is done by mounting the positive in the projection unit according to the manufacturer's instructions, and masking off sections of the screen for a series of increasing exposure time. The ideal exposure is the minimum time at which there is no loss of emulsion from the squeegee side of the screen after developing. If necessary repeat with shorter intervals to determine that time more accurately.

Factors Affecting Exposure:

- Light source and age of lamp.
- Lens thickness and diameter.
- Lens aperture.
- Distance from image to objective lens.
- Transparency of the positive background.
- Mesh and coating technique.

(The use of coloured mesh is NOT recommended as this will dramatically increase exposure time).

Developing

Gently spray both sides of the screen with cold or warm water (not above 40°C). For best results, an automated screen developing unit is recommended.

Final Drying and Spotting

Dry with the aid of a fan. Any small blemish or pinholes can be filled in using Universal Filler (FISW1) or emulsion which requires re-exposure.

Reclaiming the Screen

Remove all traces of ink with a rag soaked in an Xtend Screen Cleaner or in an automatic screen reclaiming machine using the appropriate Xtend Screen Cleaner. Rinse the screen with water and then apply diluted Strip Powder or Liquid to both sides of the stencil. Leave for a few minutes. The stencil can then be easily removed with a strong water jet or high pressure water gun. If decoating in automatic machines follow manufacturer's dilution ratios, dosing strengths and dwell times.

Standard Packing

Dirasol S10

DCS10/20	Large Jumbo Pack	20(4 x 5)ltr Emulsion
DCS10/5	Individual Pack	1 x 5ltr Emulsion

Dirasol S10 Red

DCA02/20	Large Jumbo Pack	20(4 x 5)ltr Emulsion
DCA02/5	Individual Pack	1 x 5ltr Emulsion

Dirasol SW10

DCW10/20	Large Jumbo Pack	20 (4x5) ltr Emulsion
DCW10/5	Individual Pack	1 x 5ltr Emulsion

Dirasol H10

DCH10/20	Large Jumbo Pack	20(4 x 5)ltr Emulsion
DCH10/5	Individual Pack	1 x 5ltr Emulsion

Dirasol S5

DCS05/20	Large Jumbo Pack	20(4 x 5)ltr Emulsion
DCS05/5	Individual Pack	1 x 5ltr Emulsion

Dirasol Direct Projection Emulsions

S10 - SW10 - H10 - S5 - SW5 - SUPERPRO

Dirasol SW5

DCSW5/20	Large Jumbo Pack	20(4 x 5)ltr Emulsion
DCSW5/5	Individual Pack	1 x 5ltr Emulsion

Dirasol SuperPro

DCPRO/18	Large Jumbo Pack - Emulsion and Sensitiser to make 18 (4x4.5) ltr.	
DCPRO/4500	Emulsion and Sensitiser to make 4.5 ltr.	

Storage

Dirasol emulsions should be stored in their original container with the lid firmly sealed, at the coolest possible room temperature and in no case below 0°C or above 30°C.

Safety and Handling

Dirasol Direct Project Emulsions:

- are formulated to be free from any chemicals toxic to health, carcinogenic, mutagenic or reprotoxic.
- do not have a flashpoint and is therefore exempt from the Highly Flammable Liquid Regulations.

Comprehensive information on the safety and handling of Dirasol Projection Emulsion is given in the appropriate Sericol Safety Data Sheet, available on request.

Environmental Data

Dirasol Direct Projection Emulsions:

- do not contain ozone depleting chemicals as described in the Montreal Convention.
- are formulated free from aromatic hydrocarbons which are known to have an adverse effect on the environment.
- are free of any volatile solvent and therefore beneficial to the environment when compared to solvent-based products.

The information and recommendations contained in this Product Information sheet, as well as technical advice otherwise given by representatives of our Company, whether verbally or in writing, are based on our present knowledge and believed to be accurate. However, no guarantee regarding their accuracy is given as we cannot cover or anticipate every possible application of our products and because manufacturing methods, printing stocks and other materials vary. For the same reason our products are sold without warranty and on condition that users shall make their own tests to satisfy themselves that they will meet fully their particular requirements. Our policy of continuous product improvement might make some of the information contained in this Product Information sheet out of date and users are requested to ensure that they follow current recommendations.

SERICOL
More than ink...Solutions.



SYMBOL

Subotica
Tel: +381(0) 24 643100
symbol@symbol.rs

Beograd
Tel: +381(0) 11 3478262
www.symbol.rs

GRAPHIC CENTER

Zagreb
Tel: +385(0) 1 2987044

office@graphiccenter.hr
www.graphiccenter.hr

